

Agata Nickel Laterite: Summary of Significant Intercepts

Zone	From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %
AGL-370 9950N: 10650E						
Limonite	0.00	0.85	0.85	1.07	0.059	37
Saprolite	0.85	2.90	2.05	0.87	0.013	9
AGL-374 9925N: 10625E						
Limonite	0.00	1.60	1.60	1.15	0.090	45
Saprolite	1.60	9.80	8.20	1.12	0.023	13
Saprolitic Rock	9.80	18.70	8.90	0.64	0.013	8
AGL-375 9925N: 10650E						
Ferruginous Laterite	0.00	0.95	0.95	0.52	0.025	13
Limonite	0.95	2.05	1.10	1.22	0.058	29
AGL-380 9900N: 10625E						
Limonite	0.00	1.40	1.40	1.16	0.095	49
Saprolite	1.40	17.10	15.70	1.13	0.015	8
Saprolite	26.10	28.35	2.25	1.05	0.014	8
AGL-381 9900N: 10650E						
Limonite	0.00	1.70	1.70	1.27	0.119	45
Saprolite	2.20	3.10	0.90	1.05	0.033	14
AGL-382 9900N: 10675E						
No Significant Intercept; at edge of mineralization						
AGL-385 9875N: 10600E						
Limonite	0.00	1.15	1.15	0.98	0.096	50
Saprolite	1.15	11.30	10.15	1.21	0.034	13
AGL-386 9875N: 10625E						
Limonite	0.00	2.20	2.20	1.32	0.078	45
Saprolite	2.20	30.40	28.20	1.09	0.014	8
Saprolitic Rock	30.40	31.60	1.20	0.71	0.009	6
AGL-387 9875N: 10650E						
Limonite	0.00	1.70	1.70	0.98	0.069	46
Saprolite	1.70	10.25	8.55	1.23	0.026	12
AGL-389 9850N: 10550E						
Ferruginous Laterite	0.00	1.90	1.90	0.66	0.076	48
Limonite	1.90	4.25	2.35	0.91	0.127	50
Saprolite	4.25	13.90	9.65	1.20	0.033	15
AGL-391 9850N: 10575E						
Ferruginous Laterite	0.00	1.00	1.00	0.61	0.071	46
Limonite	1.00	8.40	7.40	1.21	0.193	49
Saprolite	8.40	18.25	9.85	1.08	0.028	11
AGL-392 9850N: 10600E						
Ferruginous Laterite	0.00	2.00	2.00	0.72	0.064	49
Limonite	2.00	3.75	1.75	1.04	0.146	50
Saprolite	3.75	19.25	15.50	1.41	0.020	11
AGL-393 9850N: 10625E						
Ferruginous Laterite	0.00	1.00	1.00	0.76	0.071	49
Limonite	1.00	4.10	3.10	1.02	0.119	51
Saprolite	4.10	22.95	18.85	1.49	0.022	9
AGL-394 9850N: 10650E						
Ferruginous Laterite	0.00	1.00	1.00	0.71	0.037	51
Limonite	1.00	3.60	2.60	1.06	0.098	47
Saprolite	3.60	11.45	7.85	1.15	0.022	8

Zone	From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %
AGL-399 9750N: 10450E						
Ferruginous Laterite	0.00	2.00	2.00	0.71	0.086	46
Limonite	2.00	9.55	7.55	1.36	0.133	48
AGL-405 9700N: 10650E						
Ferruginous Laterite	0.00	3.00	3.00	0.63	0.070	49
Limonite	3.00	9.35	6.35	0.96	0.150	51
Saprolite	9.35	14.60	5.25	1.05	0.027	9
AGL-407 9650N: 10600E						
Ferruginous Laterite	0.00	2.00	2.00	0.63	0.014	49
Limonite	2.00	4.35	2.35	0.89	0.088	52
Saprolite	4.35	9.90	5.55	1.33	0.019	9
AGL-408 9650N: 10650E						
Ferruginous Laterite	0.00	1.15	1.15	0.63	0.056	48
Limonite	1.15	5.25	4.10	1.13	0.148	48
Saprolite	5.25	9.25	4.00	1.47	0.015	10
AGL-409 9600N: 10550E						
Ferruginous Laterite	0.00	2.15	2.15	0.64	0.073	49
Limonite	2.15	5.50	3.35	1.05	0.170	52
Saprolite	5.50	15.70	10.20	1.89	0.028	12
AGL-410 9600N: 10650E						
Limonite	0.00	0.90	0.90	0.95	0.123	49
Saprolite	0.90	4.20	3.30	1.06	0.013	8
AGL-411 9650N: 10700E						
No Significant Intercept; at edge of mineralization						
AGL-412 9550N: 10550E						
Ferruginous Laterite	0.00	1.75	1.75	0.70	0.058	50
Limonite	1.75	3.60	1.85	1.00	0.184	52
Saprolite	3.60	12.00	8.40	1.57	0.049	11
AGL-413 9900N: 10350E						
Limonite	0.00	2.80	2.80	1.06	0.103	48
Saprolite	2.80	4.40	1.60	1.11	0.058	24
Saprolite	9.65	16.50	6.85	0.90	0.024	11
AGL-414 9450N: 10350E						
Limonite	0.00	0.78	0.78	0.84	0.098	47
Saprolite	0.78	10.40	9.62	1.35	0.020	10
AGL-415 9750N: 10400E						
Limonite	0.00	2.50	2.50	1.05	0.141	47
Saprolite	2.50	4.60	2.10	1.79	0.028	13
AGL-416 9750N: 10350E						
Limonite	0.00	1.70	1.70	1.20	0.088	47
Saprolite	1.70	3.30	1.60	1.15	0.028	13
AGL-417 9450N: 10400E						
Ferruginous Laterite	0.00	1.00	1.00	0.66	0.047	50
Limonite	1.00	3.30	2.30	1.12	0.170	47
Saprolite	3.30	23.65	20.35	1.37	0.029	9
Saprolitic Rock	23.65	26.65	3.00	0.73	0.016	8
AGL-418 9900N: 10250E						
Ferruginous Laterite	0.00	2.00	2.00	0.65	0.056	44
Limonite	2.00	8.90	6.90	1.19	0.139	48
Saprolite	8.90	12.10	3.20	1.06	0.023	9

Zone	From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %
AGL-430 9800N: 10350E						
Ferruginous Laterite	0.00	1.20	1.20	0.61	0.023	46
Limonite	1.20	10.00	8.80	1.09	0.171	50
Saprolite	10.00	15.80	5.80	0.92	0.031	10
AGL-434 9750N: 10300E						
Ferruginous Laterite	0.00	1.85	1.85	0.68	0.040	46
Limonite	1.85	9.30	7.45	1.17	0.133	50
Saprolite	9.30	19.55	10.25	1.44	0.035	16
AGL-439 9700N: 10350E						
Ferruginous Laterite	0.00	1.60	1.60	0.72	0.037	49
Limonite	1.60	5.00	3.40	1.02	0.134	51
Saprolite	5.00	12.70	7.70	1.41	0.029	14
AGL-464 9450N: 10450E						
Ferruginous Laterite	0.00	2.90	2.90	0.66	0.061	51
Limonite	2.90	5.30	2.40	0.96	0.131	52
Saprolite	5.30	13.05	7.75	1.85	0.075	13
AGL-470 9825N: 10550E						
Ferruginous Laterite	0.00	2.15	2.15	0.62	0.072	47
Limonite	2.15	10.30	8.15	1.20	0.154	50
Saprolite	10.30	15.90	5.60	1.40	0.039	14
AGL-471 9825N: 10575E						
Ferruginous Laterite	0.00	2.50	2.50	0.62	0.082	48
Limonite	2.50	8.30	5.80	1.33	0.121	45
Saprolite	8.30	12.05	3.75	0.72	0.018	9
AGL-474 9800N: 10575E						
Ferruginous Laterite	0.00	2.85	2.85	0.59	0.084	45
Limonite	2.85	9.85	7.00	1.11	0.126	42
Saprolite	9.85	14.95	5.10	1.11	0.022	10
AGL-478 9950N: 10250E						
Ferruginous Laterite	0.00	1.10	1.10	0.74	0.043	48
Limonite	1.10	4.65	3.55	1.24	0.126	48
Saprolite	4.65	11.90	7.25	1.17	0.027	13