

Agata Nickel Laterite: Summary of Significant Intercepts

From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %	Zone
AGL-367 9975N: 10600E						
0.00	1.10	1.10	0.76	0.06	50	Ferruginous Laterite
1.10	5.35	4.25	1.07	0.09	38	Limonite
6.50	12.90	6.40	0.92	0.02	11	Saprolite
AGL-368 9950N: 10600E						
0.00	2.00	2.00	1.03	0.14	49	Limonite
2.00	11.40	9.40	1.24	0.03	14	Saprolite
AGL-369 9950N: 10625E						
0.00	3.50	3.50	0.91	0.09	49	Limonite
4.35	14.30	9.95	0.97	0.03	12	Saprolite
AGL-371 9925N: 10550E						
0.00	1.00	1.00	0.73	0.05	49	Ferruginous Laterite
1.00	2.95	1.95	1.01	0.12	50	Limonite
2.95	13.25	10.30	1.01	0.02	11	Saprolite
AGL-372 9925N: 10575E						
0.00	3.35	3.35	1.03	0.13	43	Limonite
3.95	9.85	5.90	1.24	0.03	13	Saprolite
AGL-379 9900N: 10650E						
0.00	2.60	2.60	1.29	0.09	39	Limonite
2.60	13.85	11.25	1.18	0.03	14	Saprolite
AGL-398 9800N: 10650E						
0.00	2.30	2.30	0.69	0.05	48	Ferruginous Laterite
2.30	11.70	9.40	1.17	0.19	50	Limonite
11.70	15.60	3.90	1.01	0.06	10	Saprolite
AGL-400 9750N: 10500E						
0.00	0.80	0.80	0.71	0.08	46	Ferruginous Laterite
0.80	3.55	2.75	1.13	0.12	40	Limonite
3.55	4.90	1.35	1.34	0.02	13	Saprolite
AGL-402 9750N: 10600E						
0.00	1.80	1.80	0.63	0.06	49	Ferruginous Laterite
1.80	6.00	4.20	1.26	0.19	43	Limonite
7.85	20.85	13.00	1.15	0.02	9	Saprolite
AGL-403 9750N: 10650E						
0.00	1.00	1.00	0.66	0.06	48	Ferruginous Laterite
1.00	6.70	5.70	1.17	0.16	48	Limonite
6.70	19.90	13.20	1.02	0.04	13	Saprolite
26.55	31.30	4.75	1.02	0.02	8	Saprolite
AGL-404 9700N: 10550E						
0.00	1.60	1.60	0.67	0.07	47	Ferruginous Laterite
1.60	6.25	4.65	1.14	0.13	50	Limonite
6.25	13.50	7.25	1.50	0.03	13	Saprolite
AGL-406 9650N: 10550E						
0.00	1.45	1.45	0.69	0.03	49	Ferruginous Laterite
1.45	3.65	2.20	1.03	0.14	50	Limonite
3.65	11.95	8.30	1.51	0.03	8	Saprolite
AGL-420 9900N: 10050E						
0.00	2.60	2.60	0.72	0.08	49	Ferruginous Laterite
2.60	13.65	11.05	1.02	0.12	49	Limonite
14.60	20.30	5.70	1.13	0.02	10	Saprolite
AGL-425 9850N: 10250E						
0.00	1.75	1.75	0.71	0.07	46	Ferruginous Laterite
1.75	8.10	6.35	1.18	0.11	48	Limonite

From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %	Zone
9.50	12.90	3.40	1.18	0.03	15	Saprolite
AGL-426 9850N: 10200E						
0.00	5.00	5.00	1.33	0.12	46	Limonite
5.00	6.65	1.65	1.72	0.03	14	Saprolite
AGL-428 9850N: 10100E						
0.00	3.15	3.15	0.69	0.08	46	Ferruginous Laterite
3.15	7.65	4.50	1.36	0.11	49	Limonite
7.65	12.25	4.60	1.42	0.03	15	Saprolite
14.85	21.50	6.65	0.92	0.02	11	Saprolite
AGL-429 9850N: 10050E						
0.00	0.90	0.90	0.63	0.06	48	Ferruginous Laterite
0.90	9.60	8.70	0.98	0.11	46	Limonite
9.60	14.50	4.90	1.17	0.05	22	Saprolite
AGL-431 9800N: 10250E						
0.00	0.95	0.95	0.65	0.07	44	Ferruginous Laterite
0.95	6.70	5.75	1.14	0.14	48	Limonite
6.70	11.10	4.40	2.07	0.03	16	Saprolite
AGL-432 9800N: 10150E						
0.00	7.90	7.90	1.24	0.16	48	Limonite
7.90	20.55	12.65	1.55	0.02	10	Saprolite
AGL-460 9500N: 10500E						
0.00	2.95	2.95	0.54	0.03	49	Ferruginous Laterite
2.95	5.10	2.15	0.87	0.12	53	Limonite
5.10	12.95	7.85	1.58	0.04	11	Saprolite
AGL-461 9500N: 10450E						
0.00	3.90	3.90	0.58	0.07	50	Ferruginous Laterite
3.90	8.35	4.45	1.22	0.16	48	Limonite
8.90	15.50	6.60	1.21	0.02	9	Saprolite
AGL-462 9500N: 10350E						
0.00	1.65	1.65	0.70	0.05	50	Ferruginous Laterite
1.65	4.65	3.00	1.36	0.13	45	Limonite
4.65	21.55	16.90	1.81	0.02	9	Saprolite
AGL-463 9450N: 10500E						
0.00	2.25	2.25	0.63	0.06	50	Ferruginous Laterite
2.25	4.65	2.40	0.90	0.08	54	Limonite
4.65	8.75	4.10	1.13	0.07	11	Saprolite
AGL-465 9950N: 10200E						
0.00	2.15	2.15	0.68	0.07	43	Ferruginous Laterite
2.15	5.85	3.70	1.14	0.12	43	Limonite
5.85	11.35	5.50	1.12	0.02	10	Saprolite
AGL-479 9950N: 10150E						
0.00	2.75	2.75	1.25	0.10	43	Limonite
2.75	9.35	6.60	1.10	0.03	11	Saprolite
AGL-480 9950N: 10100E						
0.00	7.20	7.20	1.11	0.13	47	Limonite
7.20	17.75	10.55	1.46	0.03	13	Saprolite