

Agata Nickel Laterite: Summary of Significant Intercepts (August 6, 2010)						
Zone	From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %
AGL-421 9900N: 10000E						
Limonite	0.00	2.20	2.20	1.14	0.09	45
Saprolite	3.15	6.45	3.30	0.99	0.04	16
AGL-433 9800N: 10050E						
Ferruginous Laterite	0.00	2.70	2.70	0.68	0.05	50
Limonite	2.70	5.20	2.50	0.88	0.17	48
Saprolite	5.20	7.35	2.15	1.09	0.06	17
AGL-435 9750N: 10250E						
Limonite	0.00	3.35	3.35	1.15	0.090	47
Saprolite	3.35	6.95	3.60	1.20	0.017	9
AGL-436 9750N: 10200E						
Limonite	0.00	4.45	4.45	1.33	0.106	45
Saprolite	4.45	14.80	10.35	1.29	0.017	10
AGL-437 9750N: 10150E						
Ferruginous Laterite	0.00	1.70	1.70	0.65	0.064	45
Limonite	1.70	5.85	4.15	1.03	0.105	46
Saprolite	5.85	21.70	15.85	1.18	0.028	15
AGL-438 9700N: 10450E						
Ferruginous Laterite	0.00	1.00	1.00	0.77	0.066	46
Limonite	1.00	4.00	3.00	1.34	0.129	48
Saprolite	4.00	5.65	1.65	2.59	0.030	18
AGL-440 9700N: 10250E						
Ferruginous Laterite	0.00	2.65	2.65	0.60	0.07	47
Limonite	2.65	7.80	5.15	1.05	0.14	51
Saprolite	7.80	14.85	7.05	1.05	0.02	9
AGL-441 9650N: 10500E						
Ferruginous Laterite	0.00	3.45	3.45	0.50	0.095	48
Limonite	3.45	10.55	7.10	1.19	0.172	51
Saprolite	10.55	20.35	9.80	1.53	0.041	15
AGL-442 9650N: 10450E						
Ferruginous Laterite	0.00	3.05	3.05	0.57	0.042	48
Limonite	3.05	10.20	7.15	1.27	0.134	48
Saprolite	10.20	13.10	2.90	1.24	0.044	19
AGL-443 9650N: 10400E						
Ferruginous Laterite	0.00	2.90	2.90	0.58	0.05	49
Limonite	2.90	6.60	3.70	0.97	0.16	47
Saprolite	7.85	11.45	3.60	1.33	0.03	13
AGL-444 9650N: 10350E						
Ferruginous Laterite	0.00	1.60	1.60	0.57	0.03	49
Limonite	1.60	3.40	1.80	0.87	0.06	51
Saprolite	3.40	9.40	6.00	1.53	0.05	9
AGL-445 9650N: 10300E						
Ferruginous Laterite	0.00	3.25	3.25	0.63	0.06	50
Limonite	3.25	10.55	7.30	1.44	0.15	45
Saprolite	10.55	18.95	8.40	1.15	0.02	11
AGL-446 9650N: 10250E						
Ferruginous Laterite	0.00	6.85	6.85	0.58	0.12	46
Limonite	6.85	12.95	6.10	1.41	0.11	44
Saprolite	12.95	15.70	2.75	1.41	0.03	20
Saprolite	19.70	21.90	2.20	0.99	0.02	10

Zone	From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %
AGL-447 9650N: 10200E						
Ferruginous Laterite	0.00	8.70	8.70	0.57	0.08	46
Limonite	8.70	9.70	1.00	1.26	0.12	50
Saprolite	9.70	18.05	8.35	1.09	0.02	10
AGL-448 9650N: 10150E						
Ferruginous Laterite	7.95	12.15	4.20	0.74	0.11	46
Limonite	12.15	15.20	3.05	1.24	0.13	51
Saprolite	15.20	19.95	4.75	1.71	0.03	15
AGL-449 9650N: 10050E						
Ferruginous Laterite	0.00	1.00	1.00	0.78	0.07	47
Saprolite	1.40	4.60	3.20	1.18	0.03	14
AGL-450 9600N: 10450E						
Ferruginous Laterite	0.00	3.30	3.30	0.61	0.03	51
Limonite	3.30	7.35	4.05	0.97	0.10	49
Saprolite	7.35	17.65	10.30	1.66	0.05	10
Saprolite	19.60	22.70	3.10	0.99	0.01	7
AGL-451 9600N: 10350E						
Ferruginous Laterite	0.00	1.75	1.75	0.65	0.06	49
Limonite	1.75	7.85	6.10	1.49	0.12	41
Saprolite	7.85	12.85	5.00	1.26	0.03	14
AGL-452 9600N: 10250E						
Ferruginous Laterite	0.00	4.25	4.25	0.53	0.08	46
Limonite	4.25	6.35	2.10	0.98	0.15	50
Saprolite	6.35	23.85	17.50	1.07	0.03	12
AGL-453 9600N: 10140E						
Limonite	1.90	12.80	10.90	1.55	0.09	40
Saprolite	13.05	18.50	5.45	1.34	0.03	16
AGL-454 9600N: 10050E						
Ferruginous Laterite	0.00	2.85	2.85	0.66	0.06	53
Limonite	2.85	3.75	0.90	1.08	0.22	51
Saprolite	3.75	13.10	9.35	1.51	0.03	15
AGL-455 10500N: 9550E						
Ferruginous Laterite	0.00	2.25	2.25	0.66	0.06	50
Limonite	2.25	4.75	2.50	0.84	0.07	52
Saprolite	4.75	12.80	8.05	1.12	0.04	10
AGL-456 9550N: 10450E						
Ferruginous Laterite	0.00	3.75	3.75	0.55	0.04	50
Limonite	3.75	5.75	2.00	0.94	0.17	52
Saprolite	5.75	18.00	12.25	1.58	0.03	13
AGL-457 9550N: 10400E						
Ferruginous Laterite	0.00	3.00	3.00	0.64	0.03	51
Limonite	3.00	5.00	2.00	1.27	0.21	47
Saprolite	5.00	9.60	4.60	0.93	0.05	14
AGL-458 9550N: 10350E						
Limonite	0.00	1.10	1.10	1.15	0.08	48
Saprolite	1.10	5.70	4.60	1.84	0.03	17
AGL-459 9550N: 10300E						
Ferruginous Laterite	0.00	1.75	1.75	0.62	0.08	49
Limonite	1.75	4.80	3.05	1.20	0.13	48
Saprolite	4.80	13.80	9.00	1.51	0.03	12

Zone	From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %
AGL-471 9825N: 10575E						
Ferruginous Laterite	0.00	2.50	2.50	0.62	0.08	48
Limonite	2.50	8.30	5.80	1.33	0.12	45
Saprolite	8.30	12.05	3.75	0.72	0.02	9
AGL-481 9950N: 10050E						
Limonite	0.00	11.00	11.00	1.18	0.14	51
Saprolite	11.00	16.75	5.75	1.59	0.03	16
AGL-483 10000N: 10150E						
Ferruginous Laterite	0.00	1.00	1.00	0.73	0.02	49
Limonite	1.00	4.15	3.15	0.95	0.04	51
Saprolite	4.15	15.00	10.85	1.28	0.04	12
AGL-484 10000N: 10050E						
Ferruginous Laterite	0.00	3.25	3.25	0.69	0.08	47
Limonite	3.25	9.45	6.20	1.31	0.14	50
Saprolite	9.45	12.75	3.30	1.47	0.03	16
AGL-485 10050N: 10200E						
Ferruginous Laterite	0.00	1.00	1.00	0.69	0.039	48
Limonite	1.00	4.65	3.65	1.11	0.128	49
Saprolite	4.65	9.80	5.15	1.01	0.037	14
AGL-486 10050N: 10150E						
Ferruginous Laterite	0.00	1.00	1.00	0.67	0.05	47
Limonite	1.00	6.75	5.75	1.19	0.16	48
Saprolite	7.45	11.05	3.60	1.05	0.02	10
AGL-487 10100N: 10150E						
Ferruginous Laterite	0.00	1.05	1.05	0.67	0.03	47
Limonite	1.05	7.25	6.20	1.31	0.13	47
Saprolite	7.25	16.95	9.70	1.10	0.03	11
AGL-488 10150N: 10200E						
Ferruginous Laterite	0.00	2.00	2.00	0.69	0.08	47
Limonite	2.00	8.30	6.30	1.23	0.15	50
Saprolite	8.30	15.90	7.60	1.31	0.07	18
AGL-489 10200N: 10150E						
Ferruginous Laterite	0.00	1.00	1.00	0.64	0.030	47
Limonite	1.00	4.55	3.55	0.98	0.113	49
Saprolite	4.55	15.55	11.00	1.04	0.041	12
AGL-490 10200N: 10100E						
Ferruginous Laterite	0.00	2.05	2.05	0.61	0.07	46
Limonite	2.05	8.80	6.75	1.08	0.11	49
Saprolite	8.80	15.80	7.00	1.15	0.04	14
AGL-491 10250N: 10200E						
Limonite	0.00	3.25	3.25	0.98	0.188	50
Saprolite	3.25	4.90	1.65	1.10	0.053	13
AGL-492 10250N: 10100E						
Ferruginous Laterite	0.00	1.20	1.20	0.60	0.03	47
Limonite	1.20	7.40	6.20	0.80	0.12	41
Saprolite	7.40	13.25	5.85	1.24	0.04	12
AGL-493 9500N: 9000E						
Limonite	0.00	3.20	3.20	0.53	0.11	31
Saprolite	3.20	12.35	9.15	1.25	0.02	11

Zone	From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %
AGL-494	9500N: 9050E					
Ferruginous Laterite	0.00	4.30	4.30	0.54	0.09	50
Limonite	4.30	6.35	2.05	0.89	0.13	53
Saprolite	6.35	15.15	8.80	1.55	0.02	8
AGL-495	9500N: 9100E					
Ferruginous Laterite	0.00	3.95	3.95	0.57	0.09	48
Limonite	3.95	5.50	1.55	0.89	0.16	52
Saprolite	5.50	17.85	12.35	1.31	0.03	15
AGL-496	9500N: 9150E					
Ferruginous Laterite	0.00	5.30	5.30	0.64	0.09	49
Limonite	5.30	11.15	5.85	1.22	0.16	45
Saprolite	11.15	20.30	9.15	1.40	0.02	10
AGL-497	9500N: 9200E					
Ferruginous Laterite	0.00	5.95	5.95	0.62	0.10	49
Limonite	5.95	9.10	3.15	1.14	0.16	50
Saprolite	9.10	18.50	9.40	1.39	0.02	9
AGL-498	9550N: 10250E					
Limonite	0.00	1.10	1.10	0.90	0.15	50
Saprolite	1.10	14.25	13.15	1.55	0.04	18
AGL-499	9550N: 9150E					
Ferruginous Laterite	0.00	4.85	4.85	0.63	0.09	48
Limonite	4.85	9.10	4.25	0.92	0.15	53
Saprolite	9.10	15.75	6.65	0.96	0.02	11
AGL-500	9550N: 9050E					
Limonite	0.00	1.15	1.15	1.18	0.083	40
Saprolite	0.00	7.15	7.15	1.29	0.014	8
AGL-501	9600N: 9300E					
Saprolite	0.00	1.15	1.15	0.91	0.06	25
AGL-502	9600N: 9250E					
Limonite	0.00	1.40	1.40	1.59	0.08	38
Saprolite	1.40	10.45	9.05	1.29	0.03	13
AGL-503	9600N: 9200E					
Limonite	0.00	2.25	2.25	1.25	0.09	41
Saprolite	2.25	7.40	5.15	1.30	0.03	16
AGL-504	9600N: 9150E					
Ferruginous Laterite	0.00	6.35	6.35	0.71	0.08	49
Limonite	6.35	10.95	4.60	0.90	0.16	52
Saprolite	10.95	14.05	3.10	1.75	0.02	11
AGL-505	9600N: 9100E					
Ferruginous Laterite	0.00	3.00	3.00	0.52	0.11	46
Limonite	3.00	4.80	1.80	1.03	0.12	49
Saprolite	4.80	16.90	12.10	1.55	0.03	13
AGL-506	9600N: 9050E					
Ferruginous Laterite	0.00	2.40	2.40	0.63	0.110	47
Saprolite	2.40	9.70	7.30	1.38	0.029	14
AGL-507	9600N: 9000E					
Ferruginous Laterite	0.00	3.25	3.25	0.72	0.085	52
Saprolite	3.25	6.40	3.15	1.45	0.093	15
AGL-508	9650N: 9350E					
Limonite	0.00	2.25	2.25	1.03	0.11	44
Saprolite	2.25	5.15	2.90	1.26	0.03	11

Zone	From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %
AGL-509 9650N: 9250E						
Ferruginous Laterite	0.00	1.00	1.00	0.73	0.06	48
Limonite	1.00	4.50	3.50	0.86	0.13	51
Saprolite	4.50	13.70	9.20	1.61	0.03	15
AGL-510 9650N: 9150E						
Ferruginous Laterite	0.00	4.20	4.20	0.68	0.04	50
Limonite	4.20	7.80	3.60	1.06	0.20	51
Saprolite	7.80	14.60	6.80	1.56	0.05	17
AGL-511 9750N: 9150E						
Limonite	0.00	3.95	3.95	1.01	0.13	49
Saprolite	3.95	16.25	12.30	1.24	0.03	12
AGL-512 9700N: 9250E						
Ferruginous Laterite	0.00	1.00	1.00	0.68	0.036	48
Limonite	1.00	5.45	4.45	0.89	0.081	51
Saprolite	6.05	13.70	7.65	1.43	0.040	12
AGL-513 9700N: 9250E						
Ferruginous Laterite	0.00	0.60	0.60	0.65	0.047	46
Limonite	0.60	5.60	5.00	1.00	0.131	49
Saprolite	5.60	17.80	12.20	1.35	0.027	13
AGL-514 9700N: 9200E						
Ferruginous Laterite	0.00	0.60	0.60	0.79	0.08	47
Limonite	0.60	4.60	4.00	1.14	0.14	46
Saprolite	4.60	8.40	3.80	0.95	0.03	14
AGL-515 9700N: 9150E						
Ferruginous Laterite	0.00	2.85	2.85	0.72	0.06	49
Limonite	2.85	6.25	3.40	0.97	0.12	46
Saprolite	6.25	15.25	9.00	1.56	0.02	12
AGL-516 9750N: 9250E						
Ferruginous Laterite	0.00	1.85	1.85	0.78	0.05	48.02
Limonite	1.85	6.50	4.65	1.42	0.15	45
Saprolite	7.90	13.80	5.90	0.99	0.03	12.33
AGL-517 9300N: 9800E						
Limonite	0.00	5.70	5.70	1.05	0.11	47
Saprolite	5.70	9.00	3.30	1.19	0.02	9
AGL-518 9250N: 9800E						
Ferruginous Laterite	0.00	2.20	2.20	0.70	0.04	48
Limonite	2.20	9.05	6.85	1.11	0.17	48
Saprolite	9.05	16.45	7.40	1.35	0.03	13
AGL-519 9800N: 9200E						
Ferruginous Laterite	0.00	1.05	1.05	0.74	0.05	48
Limonite	1.05	5.45	4.40	1.17	0.17	49
Saprolite	5.45	15.95	10.50	1.23	0.03	15
AGL-520 9800N: 9150E						
Limonite	0.00	3.40	3.40	1.04	0.12	49
Saprolite	3.40	10.20	6.80	1.31	0.03	14
AGL-521 9650N: 10250E						
Limonite	0.00	2.00	2.00	1.01	0.09	42
Saprolite	2.30	2.80	0.50	1.32	0.04	19
AGL-522 9850N: 9350E						
Limonite	0.00	4.00	4.00	1.33	0.08	40
Saprolite	4.00	9.90	5.90	1.35	0.04	15

Zone	From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %
AGL-523 9250N: 9850E						
Ferruginous Laterite	0.00	3.00	3.00	0.65	0.06	45
Limonite	3.00	11.55	8.55	1.12	0.13	49
Saprolite	11.55	20.90	9.35	1.67	0.05	16
AGL-524 9900N: 9300E						
Limonite	0.00	8.55	8.55	1.05	0.11	48
Saprolite	8.55	22.00	13.45	1.20	0.07	15
AGL-525 9900N: 9250E						
Ferruginous Laterite	0.00	4.00	4.00	0.65	0.07	44
Limonite	4.00	14.00	10.00	1.21	0.11	48
Saprolite	14.00	22.00	8.00	1.86	0.03	15
AGL-526 9725N: 10550E						
Ferruginous Laterite	0.00	2.75	2.75	0.58	0.08	46
Limonite	2.75	10.55	7.80	1.15	0.12	49
Saprolite	10.55	15.45	4.90	1.38	0.03	15
AGL-527 9725N: 10575E						
Ferruginous Laterite	0.00	1.75	1.75	0.58	0.06	46
Limonite	1.75	4.80	3.05	1.08	0.11	51
Saprolite	4.80	10.70	5.90	1.19	0.07	15
AGL-528 9725N: 10600E						
Ferruginous Laterite	0.00	2.05	2.05	0.66	0.06	49
Limonite	2.05	6.85	4.80	1.18	0.15	49
Saprolite	6.85	15.60	8.75	1.15	0.03	12
AGL-529 10625N: 9725E						
Ferruginous Laterite	0.00	2.80	2.80	0.59	0.04	48
Limonite	2.80	6.30	3.50	1.05	0.13	48
Saprolite	6.30	16.00	9.70	1.31	0.04	17
AGL-530 10650N: 9725E						
Ferruginous Laterite	0.00	2.70	2.70	0.66	0.10	48
Limonite	2.70	7.25	4.55	1.09	0.09	51
Saprolite	7.25	16.20	8.95	1.23	0.02	11
AGL-531 10675N: 9725E						
Ferruginous Laterite	0.00	1.75	1.75	0.65	0.07	48
Limonite	1.75	6.40	4.65	1.16	0.12	51
Saprolite	6.40	16.40	10.00	1.58	0.03	12
AGL-532 9700N: 10500E						
Ferruginous Laterite	0.00	2.00	2.00	0.66	0.07	48
Limonite	2.00	5.95	3.95	0.97	0.13	46
Saprolite	5.95	11.75	5.80	0.88	0.02	9
AGL-533 9750N: 10625E						
Ferruginous Laterite	0.00	1.20	1.20	0.57	0.03	48
Limonite	1.20	8.15	6.95	1.06	0.07	51
Saprolite	8.15	19.20	11.05	1.26	0.11	12
AGL-534 10675N: 9750E						
Ferruginous Laterite	0.00	1.10	1.10	0.63	0.05	48
Limonite	1.10	5.60	4.50	1.16	0.14	49
Saprolite	5.60	15.25	9.65	1.29	0.04	17
AGL-535 9775N: 10550E						
Ferruginous Laterite	0.00	3.20	3.20	0.63	0.09	47
Limonite	3.20	12.60	9.40	1.18	0.14	49
Saprolite	12.60	15.75	3.15	0.97	0.05	11

Zone	From (m)	To (m)	Thickness (m)	Ni %	Co %	Fe %
AGL-536 9775N: 10575E						
Ferruginous Laterite	1.15	2.75	1.60	0.66	0.11	49
Limonite	2.75	6.55	3.80	1.01	0.10	51
Saprolite	6.55	11.15	4.60	1.39	0.03	9
AGL-537 9775N: 10600E						
Ferruginous Laterite	0.00	3.25	3.25	0.60	0.06	49
Limonite	3.25	9.15	5.90	1.28	0.17	47
Saprolite	9.15	15.25	6.10	1.03	0.04	9
AGL-538 9775N: 10625E						
Ferruginous Laterite	0.00	2.10	2.10	0.56	0.03	48
Limonite	2.10	11.70	9.60	1.20	0.16	50
Saprolite	11.70	17.85	6.15	1.25	0.05	12
AGL-539 10650N: 9725E						
Ferruginous Laterite	0.00	2.20	2.20	0.62	0.04	48
Limonite	2.20	8.35	6.15	1.23	0.17	50
Saprolite	8.35	21.50	13.15	1.14	0.04	11
AGL-540 10700N: 9850E						
Limonite	0.00	1.05	1.05	0.85	0.13	42
AGL-541 10650N: 9800E						
Ferruginous Laterite	0.00	3.85	3.85	0.61	0.09	51
Limonite	3.85	6.45	2.60	1.51	0.18	45
Saprolite	6.45	7.85	1.40	1.41	0.03	12
AGL-542 10600N: 9750E						
Limonite	0.00	1.25	1.25	1.18	0.08	45
Saprolite	1.25	7.15	5.90	1.52	0.02	11
Saprolite	10.25	12.25	2.00	1.06	0.01	7
AGL-543 10600N: 9700E						
Saprolite	0.00	1.95	1.95	0.93	0.04	16
Saprolitic Rock	1.95	5.75	3.80	0.72	0.02	7
AGL-544 9700N: 10550E						
Limonite	0.00	1.90	1.90	1.05	0.09	41
Saprolite	1.90	9.50	7.60	1.16	0.02	9
AGL-545 10500N: 9750E						
Ferruginous Laterite	0.00	2.30	2.30	0.67	0.06	49
Limonite	2.30	4.10	1.80	1.05	0.13	46
Saprolite	4.10	17.55	13.45	1.73	0.02	10
AGL-546 9700N: 10500E						
Ferruginous Laterite	0.00	1.10	1.10	0.79	0.09	43
Limonite	1.10	2.30	1.20	1.27	0.08	43
Saprolite	2.30	3.60	1.30	0.88	0.03	14

Laterite Horizon	Average Thickness (m)	% Ni	% Co	% Fe
Ferruginous Laterite	1.99	0.63	0.07	48
Limonite	4.06	1.15	0.13	48
Saprolite	7.25	1.31	0.03	13