

16 HOLES
322 CORE ASSAYS

Laterite Horizon
Ferruginous laterite
Limonite
Saprolite
Saprolitic rock

Zone	From (m)	To (m)	Thickness (m)	% Ni	% Co	% Fe
AGL-362	9950 N: 10400 E					
Ferruginous Laterite	0.00	1.95	1.95	0.70	0.065	46
Limonite	1.95	5.25	3.30	1.09	0.129	48
Saprolite	5.25	13.75	8.50	1.37	0.022	13
Saprolitic Rock	13.75	14.55	0.80	0.55	0.013	7
AGL-363	9950 N: 10450 E					
Ferruginous Laterite	0.00	1.40	1.40	0.76	0.069	48
Limonite	1.40	4.05	2.65	1.15	0.079	50
Saprolite	4.05	15.00	10.95	0.95	0.027	13
Saprolitic Rock	15.00	23.10	8.10	0.50	0.015	8
AGL-364	9950 N: 10500 E					
Variography Hole						
Limonite	0.00	3.15	3.15	1.10	0.127	46
AGL-365	9950 N: 10550 E					
Variography Hole						
Ferruginous Laterite	0.00	1.00	1.00	0.79	0.067	49
Limonite	1.00	3.10	2.10	1.02	0.124	43
Saprolite	3.10	8.60	5.50	0.98	0.028	14
AGL-366	9950 N: 10575 E					
Variography Hole						
Ferruginous Laterite	0.00	1.10	1.10	0.67	0.052	48
Limonite	1.10	4.75	3.65	1.09	0.111	47
Saprolite	4.75	8.90	4.15	0.98	0.015	9
AGL-376	9900 N: 10450 E					
Ferruginous Laterite	0.00	1.30	1.30	0.69	0.062	47
Limonite	1.30	11.55	10.25	1.41	0.119	41
Saprolite	11.55	12.40	0.85	0.94	0.047	18
Saprolitic Rock	12.40	16.50	4.10	0.50	0.013	7
AGL-377	9900 N: 10525 E					
Variography Hole						
Ferruginous Laterite	0.00	0.50	0.50	0.67	0.048	47
Limonite	0.50	6.20	5.70	1.12	0.153	51
Saprolite	6.20	16.10	9.90	1.24	0.057	18
AGL-378	9900 N: 10550 E					
Variography Hole						
Limonite	0.00	2.50	2.50	1.41	0.083	40
Saprolite	2.50	19.25	16.75	1.26	0.020	11
AGL-383	9875 N: 10550 E					
Variography Hole						
Ferruginous Laterite	0.00	1.00	1.00	0.60	0.03	47.17
Limonite	1.00	3.30	2.30	0.88	0.06	48.44
Saprolite	3.30	14.80	11.50	1.37	0.02	11.12
Saprolitic Rock	14.80	15.85	1.05	0.76	0.07	48.35
AGL-384	9875 N: 10575 E					
Variography Hole						
Ferruginous Laterite	0.00	1.00	1.00	0.76	0.066	48
Limonite	1.00	3.20	2.20	1.14	0.150	48
Saprolite	3.20	12.35	9.15	1.46	0.021	11
Saprolitic Rock	12.35	13.00	0.65	0.69	0.010	6
AGL-388	9850 N: 10450 E					
Ferruginous Laterite	0.00	1.95	1.95	0.66	0.067	47
Limonite	1.95	7.35	5.40	1.12	0.135	50
Saprolite	7.35	14.50	7.15	1.29	0.029	14
AGL-390	9850 N: 10500 E					
Ferruginous Laterite	0.00	0.80	0.80	0.66	0.039	48
Limonite	0.80	3.95	3.15	1.00	0.146	50
Saprolite	3.95	10.00	6.05	1.52	0.022	12
AGL-395	9825 N: 10600 E					
Ferruginous Laterite	0.00	2.70	2.70	0.68	0.068	48
Limonite	2.70	9.00	6.30	1.40	0.123	46
Saprolite	9.00	23.55	14.55	1.38	0.017	7
AGL-396	9800 N: 10450 E					
Ferruginous Laterite	0.00	2.95	2.95	0.63	0.08	46.14
Limonite	2.95	10.15	7.20	1.22	0.15	47.87
Saprolite	10.15	14.15	4.00	1.21	0.02	12.18
Saprolitic Rock	14.15	16.45	2.30	0.54	0.03	8.97
AGL-397	9800 N: 10550 E					
Ferruginous Laterite	0.00	3.70	3.70	0.61	0.079	47
Limonite	3.70	8.35	4.65	1.09	0.118	48
Saprolite	8.35	11.40	3.05	0.88	0.019	10
AGL-401	9750 N: 10550 E					
Ferruginous Laterite	0.00	2.15	2.15	0.50	0.044	44
Limonite	2.15	11.25	9.10	1.12	0.137	51
Saprolite	11.25	18.85	7.60	0.99	0.028	10

Average Thickness	% Ni	% Co	% Fe
1.47	0.65	0.064	47
4.60	1.19	0.126	47
7.48	1.24	0.025	12
1.06	0.53	0.020	10